

Embossed FilmicTape ASLAN TF 105

Filmic tape with structured surface for the application of self-adhesive films

Universal application film with structured surface for a specially easy application of cut letterings, graphics and logos.

For additional information please contact our technical advisory service:
+49 (0) 22 04. 7 08-80

Construction

face-film:	PP
thickness:	~ 110 µm
adhesive:	acrylic pressure adhesive

Characteristics

adhesive strength: (ASTMD-903)	after 30 minutes	~ 0.4 N/25 mm
	after 1 week	~ 0.8 N/25 mm
tensile strength:	DIN 53 455	longitudinal: ~ 150 % lateral: ~ 150 %
temperature:	application temperature:	min. 15°C
	service temperature range:	-30 °C up to +80 °C

Processing

application:	Dry application only. Longer application processes and high temperatures increase the adhesive strength.
	To apply, turn the lettering with the tape around and remove the silicon cardboard in an angle of 180 degrees.
storage life:	As adhesives tend to dry out, the tape should be stored in its original box at room temperature and a relative humidity of 40-50 %. It should be protected from direct sunlight.

State: 10|2013

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49 (0) 2204. 708 80 · fax +49 (0) 2204. 708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN

EXPERTISE IN SELF-ADHESIVE FILMS