

EasyReflective®

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certification
PU	140 Microns	Adhesive Polyester	

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	90 gf	30cm/sec	15 Seconds	150°	Medium (5 Bar)	warm

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier warm (5-10 seconds off the press)

PRODUCT HIGHLIGHTS

- Highly reflective PU heat transfer vinyl
- Illuminates in the darkest of conditions
- Adhesive carrier makes cutting & weeding small details easy

NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble Dry	Dry Cleaning	Storage Shelf Life	Storage Temperature	Conditions	Position
Cold or warm, with mild detergent	YES Inside-out	YES Normal setting	NO	Up to 2 years	Between 18-26° C	Away from sunlight & dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations.

