



ORAJET® 3164

ORAJET® 3164 Intermediate - PVC film with polyacrylate (water-based) permanent, clear or grey adhesive. Suitable for short to medium term outdoor advertising.

Dry application only.

Available in 3164, 3164X & 3164HT

Recommended for use with ORAGUARD® Series 200 and 210 laminate.



4 Year



Available in 3164, 3164X & 3164HT



Suitable for ECO-Solvent, Solvent, UV and Latex printers



Laminate with ORAGUARD® Series 200 & 210



3164 Technical Data

Description

Soft PVC film available in transparent and white, with a glossy or matt surface

Release Paper

Silicone coated paper on one side, 135 g/m²

Adhesive

Polyacrylate, permanent, transparent

Thickness * (without paper and adhesive)	100 micron
Dimensional stability (FINAT TM 14)	Adhered to steel, no shrinkage in cross direction, in length 0,4 mm max.
Temperature resistance ***	Adhered to aluminium, -40° C to +80° C, no variation
Water resistance	Adhered to aluminium, after 48h/23° C no variation
Adhesive power *(FINAT TM 1, after 24h, stainless steel)	16 N/25 mm
Tensile strength (DIN EN ISO 527)	Along: min. 19 MPa Across: min. 19 MPa
Elongation at break (DIN EN ISO 527)	Along: min. 130% Across: min. 150%
Shelf life **	2 years
Application temperature	>+10° C
Maximum service life by specialist application Applies for vertical outdoor exposure ⁽⁴⁾	4 years (not printed)

* average ** in original packaging, at 20° C and 50% relative humidity *** normal climate of Central Europe

Note

After printing, the ink must be allowed to thoroughly dry, in order to avoid any issues when later combined with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of the selected lacquers and paints should be tested by the user, prior to the application of the material. Furthermore the application information published by ORAFOL must be considered.